



EL-301 EPOXY LAMINATING SYSTEM

PRODUCT BULLETIN



ROOM TEMP, UNFILLED
AMBER

www.CASSpolymers.com
31200 Stephenson Hwy

800.344.7776
Madison Heights MI 48071

ADTECH@CASSpolymers.com
Ph 248.588.2270 Fax 248.588.5909

DESCRIPTION

EL-301 is an unfilled epoxy laminating resin systems with excellent handling properties which will produce dimensionally accurate laminated duplications and tools. They offer maximum cloth penetration (wet-out), low viscosity, low odor, and excellent cured physical properties. The EL-301 was developed for all types of room temperature laminating and close tolerance tooling applications. This system can also be used as adhesives due to its ability to cure as a thin film creating a very strong, durable bond. Use EL-301 with ADTECH surface coat systems ES-201-PC, ES-218 and ES-204. **Typical applications include: checking and inspecting fixtures and gauges, assembly and drill fixtures, master die molds, thin film adhesive, router and trim fixtures, foundry patterns, bonding pattern and model boards and composite stretch from skin.**

HANDLING CHARACTERISTICS @ 25°C/77°F

Mix Ratio (parts by weight).....	100R/25H
Mix Ratio (parts by volume)	3.4R/1H
Density (mixed)	9.38 lbs/gal
.....	0.040 lbs/cu in
Specific Gravity (mixed)	1.12 grams/cc
Mixed Viscosity	1000-2000 cps
Work Life	23-33 minutes
Demold Time	16 hours
Complete Cure	3-5 days
Color	Amber
Shelf Life of Resin and Hardener (in original unopened containers)	2 years

PHYSICAL PROPERTIES

6 Layer, 10 Ounce Glass Fabric Laminate:

Ultimate Tensile Strength	35,300 psi
Tensile Modulus	2.34 x 10 ⁶ psi
Ultimate Flexural Strength.....	46,410 psi
Flexural Modulus	1.43 x 10 ⁶ psi

Cast Bar:

Compressive Strength.....	13,390 psi
Hardness	86 Shore D
Coefficient of Thermal Expansion	2.42 x 10 ⁻⁵ in/in/°F
Tensile Elongation.....	6.2%
Shrinkage	0.005 in/in
Heat Deflection Temperature	>80.2°C/176°F

EL-301 Tech/Revised 3/5/10
Supercedes 12/13/06

Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. Seller accepts no responsibility for results obtained by the application of seller's products or the safety and suitability of seller's products, either alone or in combination with other products. Users are advised to make their own test to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, seller delivers the products without warranty of any nature, stated or implied, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of said products, whether used alone or in combination with other products. Purchaser waives any claim against seller for direct, indirect, consequential or exemplary damages against seller, including without limitation, damage which may incur as a result of purchaser's use or misuse of the product or the products failure to conform to any particular specifications.