



**EL-320
SERIES EPOXY
LAMINATING SYSTEM
FLAME RETARDANT**

PRODUCT BULLETIN



**www.CASSpolymers.com
31200 Stephenson Hwy**

**800.344.7776
Madison Heights MI 48071**

**ADTECH@CASSpolymers.com
Ph 248.588.2270 Fax 248.588.5909**

DESCRIPTION

EL-320 is a Halogen-Free Flame Retardant Epoxy Laminating System developed for use in fabricating parts or repairs on structures which require flame retardant, self-extinguishing properties with room-temperature curing capabilities. This system has a choice of two hardeners. The EL-320 Hardener was developed for vacuum bagging or closed molded applications and the EL-320-1 (EO9-038) Hardener was developed for use in fabricating open-molded, hand laminated parts. This system does not contain PBDE or OBDE or DBDE flame retardant additives. The EL-320 system is tested to comply with FAR/JAR 25.853(a) of the Federal Aviation Standards for aircraft interiors and other areas where flame retardant performance is needed.

HANDLING CHARACTERISTICS @ 25°C/77°F

	<u>EL-320R/EL-320H</u>	<u>EL-320R/EL-320-1H</u>
Mix Ratio (parts-by-weight)	100R/10H.....	100R/16.7H
Mixed Density	1.17 gms/cc.....	1.17 gms/cc
.....	9.8 lbs/gallon.....	9.8 lbs/gallon
Mixed Viscosity	2,650 cps	1,700 cps
Work Life (220 gram mass).....	45 minutes	16 minutes
Complete Cure (both systems)	7 days @ Room-Temperature	
Accelerated Cure Schedule (both systems).....	24 hours at Room Temperature + 4 hours at 100°C/212°F	
Mixed Color (both systems)	Unfilled Light Amber	
Shelf Life Resin & Hardener (in original unopened containers).....	2 years	

TYPICAL PHYSICAL PROPERTIES (Tested Following 7 Day Cure @ 25°C/77°F)

Tensile Strength (6 ply laminate)	32,670 psi	15,300
Tensile Elongation (cast bar)	3.8%.....	4.14%
Flexural Strength (6 ply laminate)	18,550 psi	5,018 psi
Flexural Modulus (6 ply laminate)	774,000 psi	280,800 psi
Compressive Strength (cast bar).....	13,180 psi	9,437 psi
Cured Hardness (cast bar).....	80 Shore D.....	65 Shore D
Impact Strength (cast bar).....	10.64 in-lbf/in	12.15 in-lbf/in
Heat Deflection Temperature @ 66 psi (cast bar)	40°C/104°F.....	38.5 °C/101.2°F
Heat Deflection Temp @ 66 psi (cast bar + 4 hrs @ 100°C).....	61.6°C/143°F	

FAR/JAR 25.853 Flame Test (3 ply 7500 Style E-Glass)

60 second [F1]- 90° Vertical Ignition Test	Passed	Passed
12 second [F2]- 90° Vertical Ignition Test.....	Passed	Passed

TYPICAL PHYSICAL PROPERTIES (Tested Following 4 Hour Post Cure @ 100 °C/212°F)

Tensile Strength (6 ply laminate)	16,472 psi
Tensile Elongation (cast bar)	1.39%
Flexural Strength (6 ply laminate)	7,865 psi
Flexural Modulus (6 ply laminate)	1,068,000 psi
Compressive Strength (cast bar).....	18,336 psi psi
Cured Hardness (cast bar).....	80-84 Shore D
Impact Strength (cast bar).....	6.16 in-lbf/in
Heat Deflection Temperature @ 66 psi (cast bar)	58.2°C/136.9°F

EL-320 Series Tech/New 3/12/10
Supersedes 1/16/08

Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. Seller accepts no responsibility for results obtained by the application of seller's products or the safety and suitability of seller's products, either alone or in combination with other products. Users are advised to make their own test to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, seller delivers the products without warranty of any nature, stated or implied, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of said products, whether used alone or in combination with other products. Purchaser waives any claim against seller for direct, indirect, consequential or exemplary damages against seller, including without limitation, damage which may incur as a result of purchaser's use or misuse of the product or the products failure to conform to any particular specifications.