



P-11 TYPE I FRP BOND & FILL

THIXOTROPIC-FLEXIBLE
LT. BROWN

PRODUCT BULLETIN



www.CASSpolymers.com
31200 Stephenson Hwy

800.344.7776
Madison Heights MI 48071

ADTECH@CASSpolymers.com
Ph 248.588.2270 Fax 248.588.5909

DESCRIPTION

P-11 TYPE I FRP BOND & FILL, Set-Fast Filler Paste is a two-component system developed for the combined features of bonding and filling. In fiberglass-to-fiberglass, SMC-to-SMC and other applications which require non-sag (up to 1/2") thixotropic system with high physical properties, withstands impacts, a workable pot life of 20 minutes; which allows for quick completion of small or large projects. P-11 TYPE I accepts virtually all types of finishes with "no bleed-out" and is considered having low moisture characteristics. P-11 TYPE I has excellent heat and cold resistance and a high degree of chemical resistance. P-11 TYPE I can be applied in any desired thickness. **Typical applications include: boat decks to hulls, FRP composites to FRP, fiberglass to metal, metal to concrete, detail blocks to FRP, fiber auto panels, wood to wood, metal to metal and concrete to concrete bonding applications.**

HANDLING CHARACTERISTICS @ 25°C/77°F

Mix Ratio (parts by weight or volume).....	100R/2H (BPO)
Mixed Viscosity	Thixotropic Paste
Mixed Consistency	Creamy Paste
Workable Life (100 gram mass)	10-20 minutes
Finish Schedule (100 gram mass)	30 minutes
Hardness (after 1 hour)	70-80 Shore D
Shelf Life (in original unopened containers).....	1 year
Storage Requirement.....	40°F - 80°F

P 11 Type I Tech/Revised 12/8/09
Supersedes 1/8/08

Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. Seller accepts no responsibility for results obtained by the application of seller's products or the safety and suitability of seller's products, either alone or in combination with other products. Users are advised to make their own test to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, seller delivers the products without warranty of any nature, stated or implied, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of said products, whether used alone or in combination with other products. Purchaser waives any claim against seller for direct, indirect, consequential or exemplary damages against seller, including without limitation, damage which may incur as a result of purchaser's use or misuse of the product or the products failure to conform to any particular specifications.