



P-17 REDUCER RESIN

HIGH TEMP, REDUCER
RESIN FOR P-17 ONLY

PRODUCT BULLETIN



www.CASSpolymers.com
31200 Stephenson Hwy

800.344.7776
Madison Heights MI 48071

ADTECH@CASSpolymers.com
Ph 248.588.2270 Fax 248.588.5909

DESCRIPTION

The P-17 REDUCER RESIN is a high temperature polyester resin system developed to reduce the viscosity of ADTECH P-17 High Heat Resistant Filler Paste. P-17 Reducer Resin can be added to P-17 Filler in any amount to "customize" the P-17 Filler anywhere from a thin runny paste to a sprayable consistency without altering the physical properties or the quick set work life. P-17 Reducer Resin also performs very well in applications requiring a quick setting, high temperature polyester laminating resin.

HANDLING CHARACTERISTICS @ 25°C/77°F

*Mix Ratio with BPO cream hardener (parts by weight)	100R/2H
Viscosity	1,000 cps
Work Life	11 minutes
Density.....	9.10 lbs/gal
.....	0.039 lbs/cu.in
Color	Amber
Shelf Life (in original unopened containers).....	1 year
Storage Requirement.....	40°F - 80°F

*Can be used alone to thin P-17 or with 2% BPO cream hardener for laminating applications. BPO cream hardener is not sold with the P-17 Reducer Resin.

P-17RR Tech/Revised 1/22/10
Supercedes 1/9/08

Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. Seller accepts no responsibility for results obtained by the application of seller's products or the safety and suitability of seller's products, either alone or in combination with other products. Users are advised to make their own test to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, seller delivers the products without warranty of any nature, stated or implied, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of said products, whether used alone or in combination with other products. Purchaser waives any claim against seller for direct, indirect, consequential or exemplary damages against seller, including without limitation, damage which may incur as a result of purchaser's use or misuse of the product or the products failure to conform to any particular specifications.